



PERFORMANCE DATA, KRAZY GREASE NLGI 2

Properties	Test Method	Found
Color	Visual	Light Green
Texture		Smooth
Density	lb/gal@77°F	7.50
Specific Gravity	@ 77°F	0.899
Penetration	ASTM D-217@77°F	280-290
Flash Point	ASTM D-92	530°F (277°C)
Dropping Point	ASTM D-2265	>500°F(>260°C)
Corrosion Prevention Properties	ASTM D-1743@127°F	Pass
Evaporation Loss	ASTM D-972@210 °F	Nil
Viscosity of Base Oil cst@40°C cst@100°C		154.3 12.1
Water Washout	ASTM D-1264@100°F	2.8%
Four Ball Wear Test	ASTM D-2266, 40kg, 1200rpm@167°F	0.72
Low Temp Torque	ASTM D-1478@-25°F 10 min Running 60 Min	5900 1829
Oil Separation	ASTM D-1742@77°F	2.6%
Oxidation Stability	ASTM D-1742	2.0
Wheel Bearing Leakage	ASTM D-1263	0.19 grs
4-Ball EP Weld Load	ASTM D-2596	315 Pass 400 Weld
TIMKEN Load, lb	ASTM D-2509	70